

# Test Report

Report No.: CTT2603031036ENR2

Page 1 of 45

**Applicant:** AFG Media Limited

**Address:** Ground Floor The Tun, 6-8 Jacksons Entry, Edinburgh, EH8 8PJ

**Sample Received Date:** Mar. 14, 2026

**Testing Period:** Mar. 14, 2026 - Mar. 25, 2026

**Report Date:** Apr. 03, 2026

The following merchandise was (were) submitted and identified on behalf of the applicant as:

**Sample Name:** Mistletoe Elf Dress Green Kids

**Test Model No.:** MCKMEG

**ASIN:** B0C1ZQ7NWR/B0C1ZR8NZ7/B0C1ZSMH89/B0CXF4LS8D/B0CXF2NJJH/  
B0CXF4LH3Z/B0CXF6HV1K/B0CXF6MYS6

**Exported to:** US,CAN

**Other sample models of test samples:** MCKMEGL/MCKMEGM/MCKMEGS/MCKMEGNEWX/MCKMEGNEWL/MCKMEGN  
EWM/MCKMEGNEWT2/MCKMEGNEWS

**Packaging Provided:** Yes

**Test Result(s):** Please refer to next page(s).

**Test Requested and Conclusion(s):** Please refer to next page(s).

Signed for and on Behalf of CTT:



Frank/Shelly  
Technical Manager




Verification Report



Zhejiang Consumer Testing  
Technology Co., Ltd.

1-3/F., Building 5, Zone B, Shuangchuang Street, No.E21, Xinke Road, Choujiang Subdistrict, Yiwu, Jinhua, China  
(Zhejiang)  
Tel:86-0579-89986543 Fax:86-0579-89986547 Hot Line:400 6789 666  
Website:http://www.cttlab.com Email:enquiry@cttlab.com




# Test Report

Report No.:CTT2603031036ENR2

Page 2 of 45

## Test Requested and Conclusion(s):

| No. | Standard and Requirement                                                                                                                    | Conclusion(s) |
|-----|---------------------------------------------------------------------------------------------------------------------------------------------|---------------|
| 1   | ASTM F963-23<br>- Physical and Mechanical Properties                                                                                        | PASS          |
| 2   | ASTM F963-23<br>- Flammability                                                                                                              | PASS          |
| 3   | Canada Consumer Product Safety Act,<br>Toys Regulations SOR/2011-17<br>- Mechanical and Physical Properties                                 | PASS          |
| 4   | Canada Consumer Product Safety Act,<br>Toys Regulations SOR/2011-17<br>-Flammability                                                        | PASS          |
| 5   | CPSC 16 CFR 1501 -Small Parts                                                                                                               | NA            |
| 6   | CPSIA Tracking Labels for Children's Products: As Specified in<br>Consumer Product Safety Improvement Act (CPSIA) of 2008 Section<br>103    | PASS          |
| 7   | Canada Consumer Product Safety Act (CCPSA), S.C. 2010, c. 21,<br>SOR/2018-83 Consumer Products Containing Lead Regulations<br>- Lead (Pb)   | PASS          |
| 8   | SOR/2016-193 and its amendments SOR/2022-122 Surface Coating<br>Materials Regulations<br>- Lead (Pb)                                        | PASS          |
| 9   | Canada Consumer Product Safety Act, Toys Regulations,<br>SOR/2011-17 section 23<br>- Canada Soluble Heavy Metal                             | PASS          |
| 10  | Canada Consumer Product Safety Act, Toys Regulations,<br>SOR/2011-17 section 23<br>- Lead (Pb)                                              | PASS          |
| 11  | Canada Consumer Product Safety Act, Toys Regulations,<br>SOR/2011-17 section 23<br>- Mercury (Hg)                                           | PASS          |
| 12  | ASTM F963-23 Section 4.3 Toxicology<br>4.3.5.1 Paint and Surface Coating<br>- Total Lead                                                    | PASS          |
| 13  | CPSC 16 CFR 1303<br>- Total Lead                                                                                                            | PASS          |
| 14  | US Public Law 110-314 [Consumer Product Safety Improvement Act<br>of 2008(CPSIA) Sec. 101]<br>- Total Lead (Pb) in paint or surface coating | PASS          |
| 15  | Canada Consumer Product Safety Act (CCPSA), S.C. 2010, c. 21,<br>SOR/2016-188 Phthalates Regulations                                        | PASS          |



# Test Report

Report No.:CTT2603031036ENR2

Page 3 of 45

|    |                                                                                                                                                                      |      |
|----|----------------------------------------------------------------------------------------------------------------------------------------------------------------------|------|
|    | - Phthalates                                                                                                                                                         |      |
| 16 | ASTM F963-23 Section 4.3 Toxicology<br>4.3.5.1 Paint and Surface Coating<br>- Soluble heavy metal elements                                                           | PASS |
| 17 | ASTM F963-23 Section 4.3 Toxicology<br>4.3.5.2 Non-Modeling Clays<br>- Soluble heavy metal elements                                                                  | PASS |
| 18 | ASTM F963-23 Section 4.3 Toxicology<br>4.3.5.2 Small Part Metallic Material<br>- Extractable cadmium                                                                 | NA   |
| 19 | ASTM F963-23 Section 4.3 Toxicology<br>4.3.5.2 Non-metallic Materials<br>- Total Lead                                                                                | PASS |
| 20 | US Public Law 110-314 [Consumer Product Safety Improvement Act of 2008(CPSIA) Sec. 101] and 15 U.S.C. § 1278a<br>- Total Lead (Pb) in accessible substrate materials | PASS |
| 21 | ASTM F963-23, Section 4.3 Toxicology<br>4.3.8 Accessible plasticized component<br>- Phthalates                                                                       | PASS |
| 22 | US Public Law 110-314 [Consumer Product Safety Improvement Act of 2008(CPSIA) Sec. 108] and CPSC 16 CFR 1307<br>- Phthalates                                         | PASS |

NOTE: 1. NA = Not Applicable.

## Test Result(s):

Mechanical and Physical Properties - ASTM F963-23


Labeled age group: /

Appropriate age grading: 3+

Age grading for testing: 3+

Applicant's Specified Testing Age Group: 3-14 years old

| Section          | Testing Items                                              | Assessment |
|------------------|------------------------------------------------------------|------------|
|                  |                                                            | 26         |
| 4                | Safety Requirements                                        |            |
| 4.1              | Material Quality                                           | PASS       |
| 4.3.7            | Stuffing Materials                                         | NA         |
| 4.4 <sup>n</sup> | Electrical/Thermal Energy                                  | NA         |
| 4.5              | Sound-producing Toys                                       | NA         |
| 4.6              | Small Objects                                              |            |
| 4.6.1            | Toys that are intended for children under 36 months of age | NA         |




# Test Report

Report No.:CTT2603031036ENR2

Page 4 of 45

|                       |                                                                                                                      |      |
|-----------------------|----------------------------------------------------------------------------------------------------------------------|------|
| 4.6.2 <sup>n</sup>    | Mouth-actuated Toys                                                                                                  | NA   |
| 4.6.3                 | Toys and games that are intended for use by children who are at least three years old but less than six years of age | NA   |
| 4.7                   | Accessible Edges                                                                                                     | PASS |
| 4.8                   | Projections                                                                                                          | NA   |
| 4.9                   | Accessible Points                                                                                                    | PASS |
| 4.10                  | Wires or Rods                                                                                                        | NA   |
| 4.11                  | Nails and Fasteners                                                                                                  | NA   |
| 4.12                  | Plastic Film                                                                                                         | PASS |
| 4.13                  | Folding Mechanisms and Hinges                                                                                        | NA   |
| 4.14                  | Cords, Straps, and Elastics                                                                                          | NA   |
| 4.15                  | Stability and Over-Load Requirements                                                                                 | NA   |
| 4.15.1                | Stability of Ride-On Toys and Toy Seats                                                                              | NA   |
| 4.15.2                | Sideways Stability Requirements                                                                                      | NA   |
| 4.15.3                | Fore and Aft Stability                                                                                               | NA   |
| 4.15.4                | Stability of Stationary Floor Toys                                                                                   | NA   |
| 4.15.5                | Overload Requirements for Ride-On Toys and Toy Seats                                                                 | NA   |
| 4.15.6 <sup>n</sup>   | Wheeled Ride-on Toys                                                                                                 | NA   |
| 4.16                  | Confined Spaces                                                                                                      | NA   |
| 4.17                  | Wheels, Tires, and Axles                                                                                             | NA   |
| 4.18                  | Holes, Clearance, and Accessibility of Mechanisms                                                                    | NA   |
| 4.19                  | Simulated Protective Devices                                                                                         | NA   |
| 4.20                  | Pacifiers(for 4.20.2)                                                                                                | NA   |
| 4.21                  | Projectile Toys                                                                                                      | NA   |
| 4.21.1                | All Projectiles                                                                                                      | NA   |
| 4.21.2                | Projectile Toys with Stored Energy                                                                                   | NA   |
| 4.21.3                | Projectile Toys without Stored Energy                                                                                | NA   |
| 4.21.3.1 <sup>n</sup> | Mouth actuated projectile toys                                                                                       | NA   |
| 4.21.3.2              | Projectiles shall not have any sharp edges or sharp points                                                           | NA   |
| 4.21.3.3              | Arrows intended to be launched from a bow                                                                            | NA   |
| 4.21.3.4              | Projectiles in the form of an arrow                                                                                  | NA   |
| 4.21.4                | Rotors                                                                                                               | NA   |
| 4.22                  | Teethers and Teething Toys                                                                                           | NA   |
| 4.23                  | Rattles                                                                                                              | NA   |
| 4.24                  | Squeeze Toys                                                                                                         | NA   |
| 4.25                  | Battery-operated Toys(for4.25.1-4.25.8)                                                                              | NA   |




# Test Report

Report No.:CTT2603031036ENR2

Page 5 of 45

|                     |                                                                                                                                       |      |
|---------------------|---------------------------------------------------------------------------------------------------------------------------------------|------|
| 4.26                | Toys Intended to be Attached to a Crib or Playpen                                                                                     | NA   |
| 4.27                | Stuffed and Beanbag-type Toys                                                                                                         | NA   |
| 4.28                | Stroller and Carriage Toys                                                                                                            | NA   |
| 4.29                | Art Materials ( for 4.29.2 labeling)                                                                                                  | NA   |
| 4.30                | Toy Gun Marking                                                                                                                       | NA   |
| 4.31                | Balloons                                                                                                                              | NA   |
| 4.32                | Certain Toys with Nearly Spherical Ends                                                                                               | NA   |
| 4.33                | Marbles                                                                                                                               | NA   |
| 4.34                | Balls                                                                                                                                 |      |
| 4.34.1              | Toy intended for children under 36 months of age                                                                                      | NA   |
| 4.34.2              | Toys intended for children at least 3 years old but less than 8 years of age that contain a loose small ball                          | NA   |
| 4.35                | Pompoms                                                                                                                               | NA   |
| 4.36                | Hemispheric-Shaped Objects                                                                                                            | NA   |
| 4.37 <sup>n</sup>   | Yo Yo Elastic Tether Toys                                                                                                             | NA   |
| 4.38                | Magnets                                                                                                                               | NA   |
| 4.39                | Jaw Entrapment in Handles and Steering Wheels                                                                                         | NA   |
| 4.40                | Expanding Materials                                                                                                                   | NA   |
| 4.41                | Toy Chests                                                                                                                            | NA   |
| 4.41.1 <sup>n</sup> | Lid Support                                                                                                                           | NA   |
| 4.41.2              | Hinge Line Clearance                                                                                                                  | NA   |
| 4.41.3              | Closures                                                                                                                              | NA   |
| 4.41.4              | Ventilation                                                                                                                           | NA   |
| 4.41.5              | Toy chests shall comply with the requirements listed in 6.8 for accompanying instructional literature and 7.3 for producer's markings | NA   |
| 5                   | Labeling Requirement                                                                                                                  |      |
| 5.1.2               | Tracking Label                                                                                                                        | PASS |
| 5.4                 | Aquatic Toys                                                                                                                          | NA   |
| 5.5                 | Crib and Playpen Toys                                                                                                                 | NA   |
| 5.6                 | Mobiles                                                                                                                               | NA   |
| 5.7                 | Stroller and Carriage toys                                                                                                            | NA   |
| 5.8                 | Toys Intended to be Assembled By an Adult                                                                                             | NA   |
| 5.9                 | Simulated Protective Devices                                                                                                          | NA   |
| 5.10                | Toys with Functional Sharp Edges or Points                                                                                            | NA   |
| 5.11                | Small Objects, Small Balls, Marbles, and Balloons                                                                                     | NA   |



# Test Report

Report No.:CTT2603031036ENR2


Page 6 of 45

|      |                                                                                                                          |      |
|------|--------------------------------------------------------------------------------------------------------------------------|------|
| 5.12 | Art Materials                                                                                                            | NA   |
| 5.13 | Electric Toys                                                                                                            | NA   |
| 5.14 | Battery-Operated Toys                                                                                                    | NA   |
| 5.15 | Promotional Materials                                                                                                    | PASS |
| 5.16 | Magnets                                                                                                                  | NA   |
| 6    | Instructional Literature                                                                                                 |      |
| 6.1  | Definition and Description                                                                                               | PASS |
| 6.2  | Crib and Playpen Toys                                                                                                    | NA   |
| 6.3  | Mobiles                                                                                                                  | NA   |
| 6.4  | Toys Intended to be Assembled By an Adult                                                                                | NA   |
| 6.5  | Battery-Operated toys                                                                                                    | NA   |
| 6.6  | Battery-powered Ride-on Toys                                                                                             | NA   |
| 6.7  | Toys in Contact with Food                                                                                                | NA   |
| 6.8  | Toy Chests                                                                                                               | NA   |
| 6.9  | The instructional material for toys which require a manufacturer-supplied specialty or custom tool to access the battery | NA   |
| 7    | Producer's Marking                                                                                                       |      |
| 7.1  | Name of the producer or the distributor                                                                                  | PASS |
|      | Address of the producer or the distributor                                                                               | PASS |
| 7.2  | Battery-Powered Ride-on Toys                                                                                             | NA   |
| 7.3  | Toy Chests                                                                                                               | NA   |

**Note:** 1. NA = Not Applicable  
2. The above only verified the integrity and standardization of the label, excluding the verification on the authenticity of the content.

The submitted samples were undergone the use and abuse tests in accordance with the ASTM F963-23

| Testing Items | Parameter      |
|---------------|----------------|
| Impact Test   | 4×3.0 ft       |
| Torque Test   | 4.0 inch · lbf |
| Tension Test  | 15 lbf         |



# Test Report

Report No.:CTT2603031036ENR2

Page 7 of 45

## Test Result(s):

Flammability - ASTM F963-23 Annex A5

| Sample Description | Ignition Location | Burn Length (inch) | Burn Time (sec.) | Burn Rate (inch/sec.) | Limit (inch/sec.) | Conclusion |
|--------------------|-------------------|--------------------|------------------|-----------------------|-------------------|------------|
|                    |                   |                    |                  |                       |                   | 26         |
| Hat                | Edge              | 2.5                | 60               | 0.04                  | 0.15              | PASS       |
| Belt               | Edge              | 1.8                | 60               | 0.03                  | 0.15              | PASS       |
| Dress              | Edge              | 4.4                | 60               | 0.07                  | 0.15              | PASS       |
| Candy cane         | Edge              | /                  | /                | IBE                   | 0.15              | PASS       |


- Note:**
1. IBE = Ignited but self-extinguished before burn-rate could be determined.
  2. All styles of the submitted toy samples (and its accessories) was/were tested, the above result only showed the most severe burn rate of the samples.

## Test Result(s):

Flammability - ASTM F963-23 Annex A6

| Material No. | Sample Description   | Location   |
|--------------|----------------------|------------|
| 26-1         | Red non-woven fabric | Boot cover |
| 26-2         | Red and white fabric | Tight      |

| Material No. | Test Sample      |            | Plain Surface            |           |
|--------------|------------------|------------|--------------------------|-----------|
|              |                  |            | Time of Flame Spread (S) |           |
| 26-1         | --               |            | Lengthwise               | Crosswise |
|              | As Received      | 1          | DNI                      | /         |
|              |                  | 2          | DNI                      | /         |
|              |                  | 3          | DNI                      | /         |
|              |                  | 4          | DNI                      | /         |
|              |                  | 5          | DNI                      | /         |
|              |                  | Average    | /                        | /         |
|              |                  | Conclusion | PASS                     |           |
|              | After Laundering | 1          | DNI                      | /         |
|              |                  | 2          | DNI                      | /         |
|              |                  | 3          | DNI                      | /         |
|              |                  | 4          | DNI                      | /         |
|              |                  | 5          | DNI                      | /         |
|              |                  | Average    | /                        | /         |
|              |                  | Conclusion | PASS                     |           |



# Test Report

Report No.:CTT2603031036ENR2

Page 8 of 45


| Material No. | Test Sample      |            | Plain Surface            |           |
|--------------|------------------|------------|--------------------------|-----------|
|              |                  |            | Time of Flame Spread (S) |           |
| 26-2         | --               |            | Lengthwise               | Crosswise |
|              | As Received      | 1          | DNI                      | /         |
|              |                  | 2          | DNI                      | /         |
|              |                  | 3          | DNI                      | /         |
|              |                  | 4          | DNI                      | /         |
|              |                  | 5          | DNI                      | /         |
|              |                  | Average    | /                        | /         |
|              |                  | Conclusion | PASS                     |           |
|              | After Laundering | 1          | DNI                      | /         |
|              |                  | 2          | DNI                      | /         |
|              |                  | 3          | DNI                      | /         |
|              |                  | 4          | DNI                      | /         |
|              |                  | 5          | DNI                      | /         |
|              |                  | Average    | /                        | /         |
|              |                  | Conclusion | PASS                     |           |

The requirement of Plain Surface:

- 1) All specimens either did not ignite, ignited but self extinguished, or any combination thereof.  
IBE: Ignited but extinguished  
DNI: Did not ignite.
- 2) Average burn time is 3.5 s or greater.

**Remark:**

1. If only 1 of 5 specimens ignites and burns the stop cord with a time of 3.5 sec. or more, samples are acceptable.
2. If only 1 of 5 specimens ignites and burns the stop cord in less than 3.5 sec., test another set of 5 specimens. Compute the average time of flame spread for all 10 specimens. If 2 or more of these specimens ignite and burn the stop cord, average the results from those specimens. If only 1 of the 10 specimens ignites and burns the stop cord, samples are acceptable.



# Test Report

Report No.:CTT2603031036ENR2

Page 9 of 45

## Test Result(s):

Mechanical and Physical Properties - SOR/2011-17


Labeled age group: /

Appropriate age grading: 3+

Age grading for testing: 3+

Applicant's Specified Testing Age Group: 3-14 years old

| Section         | Testing Items                                                         | Assessment |
|-----------------|-----------------------------------------------------------------------|------------|
|                 |                                                                       | 26         |
| 3               | General-Official languages                                            | PASS       |
| 4               | Packaging-Flexible film bags                                          | PASS       |
| 5 <sup>n</sup>  | Electrical Hazards-Electrically operated toys                         | NA         |
| 6 <sup>n</sup>  | Electrical Hazards- Electrically heated toys                          | NA         |
| 7               | Mechanical Hazards-Small parts                                        | NA         |
| 8               | Mechanical Hazards-Metal edges                                        | NA         |
| 9               | Mechanical Hazards-Wire frames                                        | NA         |
| 10              | Mechanical Hazards-Plastic edges                                      | PASS       |
| 11              | Mechanical Hazards-Wood                                               | NA         |
| 12              | Mechanical Hazards-Glass                                              | NA         |
| 13              | Mechanical Hazards-Fasteners                                          | NA         |
| 14              | Mechanical Hazards-Safety stops or locking devices-Folding mechanisms | NA         |
| 15              | Mechanical Hazards-Spring-wound driving mechanisms                    | NA         |
| 16              | Mechanical Hazards-Projectile components                              | NA         |
| 17              | Mechanical Hazards-Enclosures                                         | NA         |
| 18              | Mechanical Hazards-Stability                                          | NA         |
| 19              | Auditory Hazards-Decibel limit                                        | NA         |
| 28              | Dolls, Plush Toys and Soft Toys-Fastenings                            | NA         |
| 29              | Dolls, Plush Toys and Soft Toys-Stuffing (a) and (b)                  | NA         |
| 30              | Dolls, Plush Toys and Soft Toys-Small parts                           | NA         |
| 31              | Dolls, Plush Toys and Soft Toys-Eyes or noses                         | NA         |
| 35              | Plant seeds-Noise                                                     | NA         |
| 36              | Plant seeds-Stuffing Material                                         | NA         |
| 37              | Pull and Push Toys-Shaft-like handle                                  | NA         |
| 38 <sup>n</sup> | Toy Steam Engines-Boilers-safety valves                               | NA         |
| 39              | Finger Paints-Water-based paints                                      | NA         |
| 40              | Rattles-Construction                                                  | NA         |
| 41              | Elastics-Length or extensibility                                      | NA         |



# Test Report

Report No.:CTT2603031036ENR2

Page 10 of 45

|                 |                                                                 |    |
|-----------------|-----------------------------------------------------------------|----|
| 42              | Yo-Yo type balls-Stretchable cords                              | NA |
| 43              | Magnetic Toys-Magnetic force                                    | NA |
| 44              | Magnetic Toys-Exceptions                                        | NA |
| 45 <sup>n</sup> | Toys Intended to be Entered by a Child-Exception                | NA |
| 46 <sup>n</sup> | Toys Intended to be Entered by a Child-Requirements and testing | NA |
| 47 <sup>n</sup> | Toys Intended to be Entered by a Child-Warning                  | NA |

**Not** 1. NA = Not Applicable.

**e:** 2. The above only verified the integrity and standardization of the label, excluding the verification on the authenticity of the content.


The submitted samples were undergone the use and abuse tests in accordance with the Canada Consumer Product Safety Act, Toys Regulations SOR/2011-17:

| Testing Items | Parameter |
|---------------|-----------|
| Drop test     | 4x0.914m  |
| Pull test     | 44.5N     |
| Push test     | 44.5N     |

## Test Result(s):

Flammability - SOR/2011-17

| Section         | Testing Items                                                   | Assessment |
|-----------------|-----------------------------------------------------------------|------------|
|                 |                                                                 | 26         |
| 21              | Flammability Hazards-Celluloid or cellulose nitrate             | PASS       |
| 32              | Dolls, Plush Toys and Soft Toys-Flammability of outer covering  | PASS       |
| 33              | Dolls, Plush Toys and Soft Toys-Flammability of yarn            | NA         |
| 34              | Dolls, Plush Toys and Soft Toys-Flammability of hair or mane    | NA         |
| 46 <sup>n</sup> | Toys Intended to be Entered by a Child-Requirements and testing | NA         |



# Test Report

Report No.:CTT2603031036ENR2


Page 11 of 45

## Test Result(s):

### Flammability

| Material No. | Sample Description   | Location   |
|--------------|----------------------|------------|
| 26-1         | Red panne            | Hat        |
| 26-2         | White fabric         | Hat        |
| 26-3         | Green panne          | Dress      |
| 26-4         | Red panne            | Dress      |
| 26-5         | White panne          | Dress      |
| 26-6         | White fabric         | Dress      |
| 26-7         | Red non-woven fabric | Boot cover |
| 26-8         | Red and white fabric | Tight      |

| Material No. | Test Sample                |            | Out Covering         |         |
|--------------|----------------------------|------------|----------------------|---------|
|              |                            |            | 1s Flame Impingement |         |
| 26-1         | Test Direction: Lengthwise |            | Flame Spread Time(s) | Remarks |
|              | As Received                | 1          | /                    | DNI     |
|              |                            | 2          | /                    | DNI     |
|              |                            | 3          | /                    | DNI     |
|              |                            | 4          | /                    | DNI     |
|              |                            | 5          | /                    | DNI     |
|              |                            | Conclusion | PASS                 |         |
|              | After Laundering           | 1          | /                    | DNI     |
|              |                            | 2          | /                    | DNI     |
|              |                            | 3          | /                    | DNI     |
|              |                            | 4          | /                    | DNI     |
|              |                            | 5          | /                    | DNI     |
|              |                            | Conclusion | PASS                 |         |




# Test Report

Report No.:CTT2603031036ENR2

Page 12 of 45

| Material No. | Test Sample                |            | Out Covering         |         |
|--------------|----------------------------|------------|----------------------|---------|
|              |                            |            | 1s Flame Impingement |         |
| 26-2         | Test Direction: Lengthwise |            | Flame Spread Time(s) | Remarks |
|              | As Received                | 1          | /                    | DNI     |
|              |                            | 2          | /                    | DNI     |
|              |                            | 3          | /                    | DNI     |
|              |                            | 4          | /                    | DNI     |
|              |                            | 5          | /                    | DNI     |
|              |                            | Conclusion | PASS                 |         |
|              | After Laundering           | 1          | /                    | DNI     |
|              |                            | 2          | /                    | IBE     |
|              |                            | 3          | /                    | DNI     |
|              |                            | 4          | /                    | IBE     |
|              |                            | 5          | /                    | DNI     |
|              |                            | Conclusion | PASS                 |         |

| Material No. | Test Sample                |            | Out Covering         |         |
|--------------|----------------------------|------------|----------------------|---------|
|              |                            |            | 1s Flame Impingement |         |
| 26-3         | Test Direction: Lengthwise |            | Flame Spread Time(s) | Remarks |
|              | As Received                | 1          | /                    | DNI     |
|              |                            | 2          | /                    | DNI     |
|              |                            | 3          | /                    | DNI     |
|              |                            | 4          | /                    | DNI     |
|              |                            | 5          | /                    | DNI     |
|              |                            | Conclusion | PASS                 |         |
|              | After Laundering           | 1          | /                    | DNI     |
|              |                            | 2          | /                    | DNI     |
|              |                            | 3          | /                    | DNI     |
|              |                            | 4          | /                    | DNI     |
|              |                            | 5          | /                    | DNI     |
|              |                            | Conclusion | PASS                 |         |




# Test Report

Report No.:CTT2603031036ENR2

Page 13 of 45

| Material No. | Test Sample                |            | Out Covering         |         |
|--------------|----------------------------|------------|----------------------|---------|
|              |                            |            | 1s Flame Impingement |         |
| 26-4         | Test Direction: Lengthwise |            | Flame Spread Time(s) | Remarks |
|              | As Received                | 1          | /                    | DNI     |
|              |                            | 2          | /                    | DNI     |
|              |                            | 3          | /                    | DNI     |
|              |                            | 4          | /                    | DNI     |
|              |                            | 5          | /                    | DNI     |
|              |                            | Conclusion | PASS                 |         |
|              | After Laundering           | 1          | /                    | DNI     |
|              |                            | 2          | /                    | DNI     |
|              |                            | 3          | /                    | DNI     |
|              |                            | 4          | /                    | DNI     |
|              |                            | 5          | /                    | DNI     |
|              |                            | Conclusion | PASS                 |         |

| Material No. | Test Sample                |            | Out Covering         |         |
|--------------|----------------------------|------------|----------------------|---------|
|              |                            |            | 1s Flame Impingement |         |
| 26-5         | Test Direction: Lengthwise |            | Flame Spread Time(s) | Remarks |
|              | As Received                | 1          | /                    | DNI     |
|              |                            | 2          | /                    | DNI     |
|              |                            | 3          | /                    | DNI     |
|              |                            | 4          | /                    | DNI     |
|              |                            | 5          | /                    | DNI     |
|              |                            | Conclusion | PASS                 |         |
|              | After Laundering           | 1          | /                    | DNI     |
|              |                            | 2          | /                    | DNI     |
|              |                            | 3          | /                    | DNI     |
|              |                            | 4          | /                    | DNI     |
|              |                            | 5          | /                    | DNI     |
|              |                            | Conclusion | PASS                 |         |




# Test Report

Report No.:CTT2603031036ENR2

Page 14 of 45

| Material No. | Test Sample                |            | Out Covering         |         |
|--------------|----------------------------|------------|----------------------|---------|
|              |                            |            | 1s Flame Impingement |         |
| 26-6         | Test Direction: Lengthwise |            | Flame Spread Time(s) | Remarks |
|              | As Received                | 1          | /                    | DNI     |
|              |                            | 2          | /                    | DNI     |
|              |                            | 3          | /                    | DNI     |
|              |                            | 4          | /                    | DNI     |
|              |                            | 5          | /                    | DNI     |
|              |                            | Conclusion | PASS                 |         |
|              | After Laundering           | 1          | /                    | DNI     |
|              |                            | 2          | /                    | DNI     |
|              |                            | 3          | /                    | DNI     |
|              |                            | 4          | /                    | DNI     |
|              |                            | 5          | /                    | DNI     |
|              |                            | Conclusion | PASS                 |         |

| Material No. | Test Sample                |            | Out Covering         |         |
|--------------|----------------------------|------------|----------------------|---------|
|              |                            |            | 1s Flame Impingement |         |
| 26-7         | Test Direction: Lengthwise |            | Flame Spread Time(s) | Remarks |
|              | As Received                | 1          | /                    | DNI     |
|              |                            | 2          | /                    | DNI     |
|              |                            | 3          | /                    | DNI     |
|              |                            | 4          | /                    | DNI     |
|              |                            | 5          | /                    | DNI     |
|              |                            | Conclusion | PASS                 |         |
|              | After Laundering           | 1          | /                    | DNI     |
|              |                            | 2          | /                    | DNI     |
|              |                            | 3          | /                    | DNI     |
|              |                            | 4          | /                    | DNI     |
|              |                            | 5          | /                    | DNI     |
|              |                            | Conclusion | PASS                 |         |



# Test Report

Report No.:CTT2603031036ENR2


Page 15 of 45

| Material No. | Test Sample                |            | Out Covering         |         |
|--------------|----------------------------|------------|----------------------|---------|
|              |                            |            | 1s Flame Impingement |         |
| 26-8         | Test Direction: Lengthwise |            | Flame Spread Time(s) | Remarks |
|              | As Received                | 1          | /                    | DNI     |
|              |                            | 2          | /                    | DNI     |
|              |                            | 3          | /                    | DNI     |
|              |                            | 4          | /                    | DNI     |
|              |                            | 5          | /                    | DNI     |
|              |                            | Conclusion | PASS                 |         |
|              | After Laundering           | 1          | /                    | DNI     |
|              |                            | 2          | /                    | DNI     |
|              |                            | 3          | /                    | DNI     |
|              |                            | 4          | /                    | DNI     |
|              |                            | 5          | /                    | DNI     |
|              |                            | Conclusion | PASS                 |         |

## Requirement for Out Covering:

- 1.If the burn time is greater than 7.0s, the sample is considered to have passed the test.
- 2.If specimen did not ignite or ignited but self-extinguished, it is considered to have passed the test.
- 3.If one of the five specimens fails, test five additional specimens. Two failures out of 10 specimens results in a failure of the product to pass the test requirement.

- Note:**
1. DNI: Did not ignite.
  2. IBE: Ignited but extinguished.



# Test Report

Report No.:CTT2603031036ENR2

Page 16 of 45

## Test Result(s):

CPSC 16 CFR 1501- Small Parts

Labeled age group: /  
 Appropriate age grading: 3+  
 Age grading for testing: 3+  
 Applicant's Specified Testing Age Group: 3-14 years old

| Test Item(s)                 | Requirements of Standard                                                                                                                                                                                                                                        | Assessment |
|------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------|
|                              |                                                                                                                                                                                                                                                                 | 26         |
| CPSC 16 CFR 1501-Small parts | Toys and other article intended for use by children under 3 years of age shall not have small parts since it presents a choking, aspiration, or ingestion hazard. Toys and other article are subject to this requirement before or after use and abuse testing. | NA         |


- Note:**
1. NA = Not Applicable.
  2. The above-mentioned evaluation only comply with the received sample.

## Test Result(s):

CPSIA Tracking Labels for Children's Products (Visual)

Method: As Specified in Consumer Product Safety Improvement Act (CPSIA) of 2008 Section 103  
 Tracking label on the packaging <sup>1</sup>

| Requirement                                                                                                               | Result  |
|---------------------------------------------------------------------------------------------------------------------------|---------|
|                                                                                                                           | 26      |
| Name of the manufacture or the name of the private labeler.                                                               | Present |
| Manufacture location, including the name of the city and country, or the name of other means of coding of city and state. | Present |
| Date of the production of the product, in a form of Month/ Year or any other coding system.                               | Present |
| The cohort information(including the batch, run number, or other identifying characteristic.                              | Present |
| Permanent remark                                                                                                          | *       |



# Test Report

Report No.:CTT2603031036ENR2

Page 17 of 45

Tracking label on the product <sup>1</sup>

| Requirement                                                                                                              | Result  |
|--------------------------------------------------------------------------------------------------------------------------|---------|
|                                                                                                                          | 26      |
| Name of the manufacture or the name of the private labeler                                                               | Present |
| Manufacture location, including the name of the city and country, or the name of other means of coding of city and state | Present |
| Date of the production of the product, in a form of Month/ Year or any other coding system                               | Present |
| The cohort information(including the batch, run number, or other identifying characteristic                              | Present |
| Permanent remark                                                                                                         | *       |


- Note:**
1. The above only verified the integrity and standardization of the label, excluding the verification on the authenticity of the content.
  2. \*=The client only provided artwork, the "Permanent remark" was not verified.

## Test Result(s):

Lead (Pb) - Canada Consumer Product Safety Act (CCPSA), S.C. 2010, c. 21, SOR/2018-83 Consumer Products Containing Lead Regulations<sup>5</sup>

| Substances    | Lead (Pb)      | Conclusion |
|---------------|----------------|------------|
| CAS No.       | 7439-92-1      |            |
| LOQ (mg/kg)   | 10             |            |
| Limit (mg/kg) | 90             |            |
| Material No.  | Result (mg/kg) |            |
| 25D           | N.D.           | PASS       |

- NOTE:**
1. mg/kg = milligram per kilogram (ppm).
  2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).
  3. "D" = The sample(s) is(are) tested according to the method Canada Method C02.2:2022.



# Test Report

Report No.:CTT2603031036ENR2

Page 18 of 45

## Test Result(s):

Lead (Pb) - SOR/2016-193 and its amendments SOR/2022-122 Surface Coating Materials Regulations<sup>s</sup>

| Substances    | Lead (Pb)      | Conclusion |
|---------------|----------------|------------|
| CAS No.       | 7439-92-1      |            |
| LOQ (mg/kg)   | 10             |            |
| Limit (mg/kg) | 90             |            |
| Material No.  | Result (mg/kg) |            |
| 25D           | N.D.           | PASS       |

- NOTE:**
1. mg/kg = milligram per kilogram (ppm).
  2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).
  3. "D" = The sample(s) is(are) tested according to the method Canada Method C02.2:2022.


## Test Result(s):

Canada Soluble Heavy Metal - Canada Consumer Product Safety Act, Toys Regulations, SOR/2011-17 section 23

Method: Canada Method C08.1(2022)<sup>s</sup>

| No.        | Substances Name       | CAS No.   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |
|------------|-----------------------|-----------|---------------|-------------|----------------|
|            |                       |           |               |             | 25             |
| 1          | Soluble Antimony (Sb) | 7440-36-0 | 1000          | 5           | N.D.           |
| 2          | Soluble Arsenic (As)  | 7440-38-2 | 1000          | 5           | N.D.           |
| 3          | Soluble Barium (Ba)   | 7440-39-3 | 1000          | 5           | N.D.           |
| 4          | Soluble Cadmium (Cd)  | 7440-43-9 | 1000          | 5           | N.D.           |
| 5          | Soluble Selenium (Se) | 7782-49-2 | 1000          | 5           | N.D.           |
| Conclusion |                       |           |               |             | PASS           |

- NOTE:**
1. mg/kg = milligram per kilogram (ppm).
  2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).



# Test Report

Report No.: CTT2603031036ENR2

Page 19 of 45

## Test Result(s):

Lead (Pb) - Canada Consumer Product Safety Act, Toys Regulations, SOR/2011-17 section 23

Method: Canada Method C02.2:2022<sup>s</sup>

| Substances    | Lead (Pb)      | Conclusion |
|---------------|----------------|------------|
| CAS No.       | 7439-92-1      |            |
| LOQ (mg/kg)   | 10             |            |
| Limit (mg/kg) | 90             |            |
| Material No.  | Result (mg/kg) |            |
| 25            | N.D.           | PASS       |

- NOTE:**
1. mg/kg = milligram per kilogram (ppm).
  2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).

## Test Result(s):

Mercury (Hg) - Canada Consumer Product Safety Act, Toys Regulations, SOR/2011-17 section 23

Method: ISO 8124-5:2015<sup>s</sup>

| Substances    | Mercury (Hg)   | Conclusion |
|---------------|----------------|------------|
| CAS No.       | 7439-97-6      |            |
| LOQ (mg/kg)   | 10             |            |
| Limit (mg/kg) | 10             |            |
| Material No.  | Result (mg/kg) |            |
| 25            | N.D.           | PASS       |


- NOTE:**
1. mg/kg = milligram per kilogram (ppm).
  2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).

## Test Result(s):

Total Lead (Pb) in paint or surface coating - US Public Law 110-314 [Consumer Product Safety Improvement Act of 2008(CPSIA) Sec. 101]<sup>s</sup>

| Substances    | Lead (Pb)      | Conclusion |
|---------------|----------------|------------|
| CAS No.       | 7439-92-1      |            |
| LOQ (mg/kg)   | 10             |            |
| Limit (mg/kg) | 90             |            |
| Material No.  | Result (mg/kg) |            |
| 25D           | N.D.           | PASS       |

- NOTE:**
1. mg/kg = milligram per kilogram (ppm).
  2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).
  3. "D" = The sample(s) is(are) tested according to the method Canada Method C02.2:2022.



# Test Report

Report No.:CTT2603031036ENR2

Page 20 of 45

## Test Result(s):

Total Lead - ASTM F963-23 Section 4.3 Toxicology 4.3.5.1 Paint and Surface Coating<sup>s</sup>

| Substances    | Lead (Pb)      | Conclusion |
|---------------|----------------|------------|
| CAS No.       | 7439-92-1      |            |
| LOQ (mg/kg)   | 10             |            |
| Limit (mg/kg) | 90             |            |
| Material No.  | Result (mg/kg) |            |
| 25D           | N.D.           | PASS       |

- NOTE:**
1. mg/kg = milligram per kilogram (ppm).
  2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).
  3. "D" = The sample(s) is(are) tested according to the method Canada Method C02.2:2022.

## Test Result(s):

Total Lead - CPSC 16 CFR 1303<sup>s</sup>


| Substances    | Lead (Pb)      | Conclusion |
|---------------|----------------|------------|
| CAS No.       | 7439-92-1      |            |
| LOQ (mg/kg)   | 10             |            |
| Limit (mg/kg) | 90             |            |
| Material No.  | Result (mg/kg) |            |
| 25D           | N.D.           | PASS       |

- NOTE:**
1. mg/kg = milligram per kilogram (ppm).
  2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).
  3. "D" = The sample(s) is(are) tested according to the method Canada Method C02.2:2022.

## Test Result(s):

Lead (Pb) - Canada Consumer Product Safety Act (CCPSA), S.C. 2010, c. 21, SOR/2018-83 Consumer Products Containing Lead Regulations

| Substances    | Lead (Pb)      | Conclusion |
|---------------|----------------|------------|
| CAS No.       | 7439-92-1      |            |
| LOQ (mg/kg)   | 10             |            |
| Limit (mg/kg) | 90             |            |
| Material No.  | Result (mg/kg) |            |
| 6R            | N.D.           | PASS       |
| 13R           | N.D.           | PASS       |
| 14D           | N.D.           | PASS       |
| 15D           | N.D.           | PASS       |



# Test Report

Report No.:CTT2603031036ENR2

Page 21 of 45

|           |      |      |
|-----------|------|------|
| 16D       | N.D. | PASS |
| (18+21)D  | N.D. | PASS |
| (23+24)D* | N.D. | PASS |
| 27R       | N.D. | PASS |


**NOTE:**

1. mg/kg = milligram per kilogram (ppm).
2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).
3. "+" = The "+" in the test sample description indicates a mixed test. The test results are the overall results of the mixed materials. The individual result of one or more materials in the mixed material may be greater than the mixed test result. Conclusion of compliance also applies to the individual materials in a mixed test only if multiplying the LOQ (Limit of Quantitation) and the number of mixed materials is less than the limit.
4. "R" = The test result is referred from identical material of other report according to applicant's request.
5. 6R = This data is refer to data of CTT2603031035EN-10.
6. 13R = This data is refer to data of CTT2603031033EN-3.
7. 27R = This data is refer to data of CTT2603031033EN-12.
8. "D" = The sample(s) is(are) tested according to the method CPSC-CH-E1002-08.3.
9. "\*" = The test sample(s) is received on Mar. 24, 2026.

**Test Result(s):**

Phthalates - Canada Consumer Product Safety Act (CCPSA), S.C. 2010, c. 21, SOR/2016-188 Phthalates Regulations

| No.        | Substances Name                                      | CAS No.                   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |      |
|------------|------------------------------------------------------|---------------------------|---------------|-------------|----------------|------|
|            |                                                      |                           |               |             | 6R             | 13R  |
| 1          | Bis(2-ethylhexyl) phthalate (DEHP)                   | 117-81-7                  | 1000          | 50          | N.D.           | N.D. |
| 2          | Butyl benzyl phthalate (BBP)                         | 85-68-7                   | 1000          | 50          | N.D.           | N.D. |
| 3          | Di-butyl phthalate (DBP)                             | 84-74-2                   | 1000          | 50          | N.D.           | N.D. |
| 4          | Diisodecyl phthalate (DIDP) <sup>n</sup>             | 26761-40-0/<br>68515-49-1 | 1000          | 100         | N.D.           | N.D. |
| 5          | Diisononyl phthalate (DINP)                          | 28553-12-0/<br>68515-48-0 | 1000          | 100         | N.D.           | N.D. |
| 6          | Phthalic acid, bis-n-octyl ester (DNOP) <sup>n</sup> | 117-84-0                  | 1000          | 50          | N.D.           | N.D. |
| Conclusion |                                                      |                           |               |             | PASS           | PASS |




# Test Report

Report No.:CTT2603031036ENR2

Page 22 of 45

| No.        | Substances Name                                      | CAS No.                   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |      |
|------------|------------------------------------------------------|---------------------------|---------------|-------------|----------------|------|
|            |                                                      |                           |               |             | 14D            | 15D  |
| 1          | Bis(2-ethylhexyl) phthalate (DEHP)                   | 117-81-7                  | 1000          | 50          | 112            | N.D. |
| 2          | Butyl benzyl phthalate (BBP)                         | 85-68-7                   | 1000          | 50          | N.D.           | N.D. |
| 3          | Di-butyl phthalate (DBP)                             | 84-74-2                   | 1000          | 50          | N.D.           | N.D. |
| 4          | Diisodecyl phthalate (DIDP) <sup>n</sup>             | 26761-40-0/<br>68515-49-1 | 1000          | 100         | N.D.           | N.D. |
| 5          | Diisononyl phthalate (DINP)                          | 28553-12-0/<br>68515-48-0 | 1000          | 100         | N.D.           | N.D. |
| 6          | Phthalic acid, bis-n-octyl ester (DNOP) <sup>n</sup> | 117-84-0                  | 1000          | 50          | N.D.           | N.D. |
| Conclusion |                                                      |                           |               |             | PASS           | PASS |

| No.        | Substances Name                                      | CAS No.                   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |          |
|------------|------------------------------------------------------|---------------------------|---------------|-------------|----------------|----------|
|            |                                                      |                           |               |             | 16D            | (18+21)D |
| 1          | Bis(2-ethylhexyl) phthalate (DEHP)                   | 117-81-7                  | 1000          | 50          | N.D.           | N.D.     |
| 2          | Butyl benzyl phthalate (BBP)                         | 85-68-7                   | 1000          | 50          | N.D.           | N.D.     |
| 3          | Di-butyl phthalate (DBP)                             | 84-74-2                   | 1000          | 50          | N.D.           | N.D.     |
| 4          | Diisodecyl phthalate (DIDP) <sup>n</sup>             | 26761-40-0/<br>68515-49-1 | 1000          | 100         | N.D.           | N.D.     |
| 5          | Diisononyl phthalate (DINP)                          | 28553-12-0/<br>68515-48-0 | 1000          | 100         | N.D.           | N.D.     |
| 6          | Phthalic acid, bis-n-octyl ester (DNOP) <sup>n</sup> | 117-84-0                  | 1000          | 50          | N.D.           | N.D.     |
| Conclusion |                                                      |                           |               |             | PASS           | PASS     |



# Test Report

Report No.:CTT2603031036ENR2


Page 23 of 45

| No.        | Substances Name                                      | CAS No.                   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |           |
|------------|------------------------------------------------------|---------------------------|---------------|-------------|----------------|-----------|
|            |                                                      |                           |               |             | 20             | (23+24)D* |
| 1          | Bis(2-ethylhexyl) phthalate (DEHP)                   | 117-81-7                  | 1000          | 50          | N.D.           | 143       |
| 2          | Butyl benzyl phthalate (BBP)                         | 85-68-7                   | 1000          | 50          | N.D.           | N.D.      |
| 3          | Di-butyl phthalate (DBP)                             | 84-74-2                   | 1000          | 50          | N.D.           | N.D.      |
| 4          | Diisodecyl phthalate (DIDP) <sup>n</sup>             | 26761-40-0/<br>68515-49-1 | 1000          | 100         | N.D.           | N.D.      |
| 5          | Diisononyl phthalate (DINP)                          | 28553-12-0/<br>68515-48-0 | 1000          | 100         | N.D.           | N.D.      |
| 6          | Phthalic acid, bis-n-octyl ester (DNOP) <sup>n</sup> | 117-84-0                  | 1000          | 50          | N.D.           | N.D.      |
| Conclusion |                                                      |                           |               |             | PASS           | PASS      |

| No.        | Substances Name                                      | CAS No.                   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |      |
|------------|------------------------------------------------------|---------------------------|---------------|-------------|----------------|------|
|            |                                                      |                           |               |             | 25D            | 27R  |
| 1          | Bis(2-ethylhexyl) phthalate (DEHP)                   | 117-81-7                  | 1000          | 50          | 72             | N.D. |
| 2          | Butyl benzyl phthalate (BBP)                         | 85-68-7                   | 1000          | 50          | N.D.           | N.D. |
| 3          | Di-butyl phthalate (DBP)                             | 84-74-2                   | 1000          | 50          | 225            | N.D. |
| 4          | Diisodecyl phthalate (DIDP) <sup>n</sup>             | 26761-40-0/<br>68515-49-1 | 1000          | 100         | N.D.           | N.D. |
| 5          | Diisononyl phthalate (DINP)                          | 28553-12-0/<br>68515-48-0 | 1000          | 100         | N.D.           | N.D. |
| 6          | Phthalic acid, bis-n-octyl ester (DNOP) <sup>n</sup> | 117-84-0                  | 1000          | 50          | N.D.           | N.D. |
| Conclusion |                                                      |                           |               |             | PASS           | PASS |

**NOTE:**

1. mg/kg = milligram per kilogram (ppm).
2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).
3. "+" = The "+" in the test sample description indicates a mixed test. The test results are the overall results of the mixed materials. The individual result of one or more materials in the mixed



# Test Report

Report No.:CTT2603031036ENR2

Page 24 of 45

material may be greater than the mixed test result. Conclusion of compliance also applies to the individual materials in a mixed test only if multiplying the LOQ (Limit of Quantitation) and the number of mixed materials is less than the limit.

4. "R" = The test result is referred from identical material of other report according to applicant's request.

5. 6R = This data is refer to data of CTT2603031035EN-10.

6. 13R = This data is refer to data of CTT2603031033EN-3.

7. 27R = This data is refer to data of CTT2603031033EN-12.

8. "D" = The sample(s) is(are) tested according to the method CPSC-CH-C1001-09.4 (2018).

9. "\*" = The test sample(s) is received on Mar. 24, 2026.

## Test Result(s):

Soluble heavy metal elements - ASTM F963-23 Section 4.3 Toxicology 4.3.5.1 Paint and Surface Coating


Method: ASTM F963-23

| No.        | Substances Name       | CAS No.   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |
|------------|-----------------------|-----------|---------------|-------------|----------------|
|            |                       |           |               |             | 25             |
| 1          | Soluble Antimony (Sb) | 7440-36-0 | 60            | 5           | N.D.           |
| 2          | Soluble Arsenic (As)  | 7440-38-2 | 25            | 2.5         | N.D.           |
| 3          | Soluble Barium (Ba)   | 7440-39-3 | 1000          | 5           | N.D.           |
| 4          | Soluble Cadmium (Cd)  | 7440-43-9 | 75            | 5           | N.D.           |
| 5          | Soluble Chromium (Cr) | 7440-47-3 | 60            | 5           | N.D.           |
| 6          | Soluble Lead (Pb)     | 7439-92-1 | 90            | 5           | N.D.           |
| 7          | Soluble Mercury (Hg)  | 7439-97-6 | 60            | 5           | N.D.           |
| 8          | Soluble Selenium (Se) | 7782-49-2 | 500           | 5           | N.D.           |
| Conclusion |                       |           |               |             | PASS           |

## NOTE:

1. mg/kg = milligram per kilogram (ppm).

2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).



# Test Report

Report No.:CTT2603031036ENR2

Page 25 of 45


## Test Result(s):

Soluble heavy metal elements - ASTM F963-23 Section 4.3 Toxicology 4.3.5.2 Non-Modeling Clays

Method: ASTM F963-23

| No.        | Substances Name       | CAS No.   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |      |
|------------|-----------------------|-----------|---------------|-------------|----------------|------|
|            |                       |           |               |             | 1              | 2    |
| 1          | Soluble Antimony (Sb) | 7440-36-0 | 60            | 5           | N.D.           | N.D. |
| 2          | Soluble Arsenic (As)  | 7440-38-2 | 25            | 2.5         | N.D.           | N.D. |
| 3          | Soluble Barium (Ba)   | 7440-39-3 | 1000          | 5           | N.D.           | N.D. |
| 4          | Soluble Cadmium (Cd)  | 7440-43-9 | 75            | 5           | N.D.           | N.D. |
| 5          | Soluble Chromium (Cr) | 7440-47-3 | 60            | 5           | N.D.           | N.D. |
| 6          | Soluble Lead (Pb)     | 7439-92-1 | 90            | 5           | N.D.           | N.D. |
| 7          | Soluble Mercury (Hg)  | 7439-97-6 | 60            | 5           | N.D.           | N.D. |
| 8          | Soluble Selenium (Se) | 7782-49-2 | 500           | 5           | N.D.           | N.D. |
| Conclusion |                       |           |               |             | PASS           | PASS |

| No.        | Substances Name       | CAS No.   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |      |
|------------|-----------------------|-----------|---------------|-------------|----------------|------|
|            |                       |           |               |             | 3              | 4    |
| 1          | Soluble Antimony (Sb) | 7440-36-0 | 60            | 5           | N.D.           | N.D. |
| 2          | Soluble Arsenic (As)  | 7440-38-2 | 25            | 2.5         | N.D.           | N.D. |
| 3          | Soluble Barium (Ba)   | 7440-39-3 | 1000          | 5           | N.D.           | N.D. |
| 4          | Soluble Cadmium (Cd)  | 7440-43-9 | 75            | 5           | N.D.           | N.D. |
| 5          | Soluble Chromium (Cr) | 7440-47-3 | 60            | 5           | N.D.           | N.D. |
| 6          | Soluble Lead (Pb)     | 7439-92-1 | 90            | 5           | N.D.           | N.D. |
| 7          | Soluble Mercury (Hg)  | 7439-97-6 | 60            | 5           | N.D.           | N.D. |
| 8          | Soluble Selenium (Se) | 7782-49-2 | 500           | 5           | N.D.           | N.D. |
| Conclusion |                       |           |               |             | PASS           | PASS |




# Test Report

Report No.:CTT2603031036ENR2

Page 26 of 45

| No.        | Substances Name       | CAS No.   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |      |
|------------|-----------------------|-----------|---------------|-------------|----------------|------|
|            |                       |           |               |             | 5              | 6R   |
| 1          | Soluble Antimony (Sb) | 7440-36-0 | 60            | 5           | N.D.           | N.D. |
| 2          | Soluble Arsenic (As)  | 7440-38-2 | 25            | 2.5         | N.D.           | N.D. |
| 3          | Soluble Barium (Ba)   | 7440-39-3 | 1000          | 5           | N.D.           | N.D. |
| 4          | Soluble Cadmium (Cd)  | 7440-43-9 | 75            | 5           | N.D.           | N.D. |
| 5          | Soluble Chromium (Cr) | 7440-47-3 | 60            | 5           | N.D.           | N.D. |
| 6          | Soluble Lead (Pb)     | 7439-92-1 | 90            | 5           | N.D.           | N.D. |
| 7          | Soluble Mercury (Hg)  | 7439-97-6 | 60            | 5           | N.D.           | N.D. |
| 8          | Soluble Selenium (Se) | 7782-49-2 | 500           | 5           | N.D.           | N.D. |
| Conclusion |                       |           |               |             | PASS           | PASS |

| No.        | Substances Name       | CAS No.   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |      |
|------------|-----------------------|-----------|---------------|-------------|----------------|------|
|            |                       |           |               |             | 7              | 8    |
| 1          | Soluble Antimony (Sb) | 7440-36-0 | 60            | 5           | N.D.           | N.D. |
| 2          | Soluble Arsenic (As)  | 7440-38-2 | 25            | 2.5         | N.D.           | N.D. |
| 3          | Soluble Barium (Ba)   | 7440-39-3 | 1000          | 5           | N.D.           | N.D. |
| 4          | Soluble Cadmium (Cd)  | 7440-43-9 | 75            | 5           | N.D.           | N.D. |
| 5          | Soluble Chromium (Cr) | 7440-47-3 | 60            | 5           | N.D.           | N.D. |
| 6          | Soluble Lead (Pb)     | 7439-92-1 | 90            | 5           | N.D.           | N.D. |
| 7          | Soluble Mercury (Hg)  | 7439-97-6 | 60            | 5           | N.D.           | N.D. |
| 8          | Soluble Selenium (Se) | 7782-49-2 | 500           | 5           | N.D.           | N.D. |
| Conclusion |                       |           |               |             | PASS           | PASS |




# Test Report

Report No.:CTT2603031036ENR2

Page 27 of 45

| No.        | Substances Name       | CAS No.   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |      |
|------------|-----------------------|-----------|---------------|-------------|----------------|------|
|            |                       |           |               |             | 9              | 10   |
| 1          | Soluble Antimony (Sb) | 7440-36-0 | 60            | 5           | N.D.           | N.D. |
| 2          | Soluble Arsenic (As)  | 7440-38-2 | 25            | 2.5         | N.D.           | N.D. |
| 3          | Soluble Barium (Ba)   | 7440-39-3 | 1000          | 5           | N.D.           | N.D. |
| 4          | Soluble Cadmium (Cd)  | 7440-43-9 | 75            | 5           | N.D.           | N.D. |
| 5          | Soluble Chromium (Cr) | 7440-47-3 | 60            | 5           | N.D.           | N.D. |
| 6          | Soluble Lead (Pb)     | 7439-92-1 | 90            | 5           | N.D.           | N.D. |
| 7          | Soluble Mercury (Hg)  | 7439-97-6 | 60            | 5           | N.D.           | N.D. |
| 8          | Soluble Selenium (Se) | 7782-49-2 | 500           | 5           | N.D.           | N.D. |
| Conclusion |                       |           |               |             | PASS           | PASS |

| No.        | Substances Name       | CAS No.   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |      |
|------------|-----------------------|-----------|---------------|-------------|----------------|------|
|            |                       |           |               |             | 11             | 12R  |
| 1          | Soluble Antimony (Sb) | 7440-36-0 | 60            | 5           | N.D.           | N.D. |
| 2          | Soluble Arsenic (As)  | 7440-38-2 | 25            | 2.5         | N.D.           | N.D. |
| 3          | Soluble Barium (Ba)   | 7440-39-3 | 1000          | 5           | 15             | N.D. |
| 4          | Soluble Cadmium (Cd)  | 7440-43-9 | 75            | 5           | N.D.           | N.D. |
| 5          | Soluble Chromium (Cr) | 7440-47-3 | 60            | 5           | N.D.           | N.D. |
| 6          | Soluble Lead (Pb)     | 7439-92-1 | 90            | 5           | N.D.           | N.D. |
| 7          | Soluble Mercury (Hg)  | 7439-97-6 | 60            | 5           | N.D.           | N.D. |
| 8          | Soluble Selenium (Se) | 7782-49-2 | 500           | 5           | N.D.           | N.D. |
| Conclusion |                       |           |               |             | PASS           | PASS |




# Test Report

Report No.:CTT2603031036ENR2

Page 28 of 45

| No.        | Substances Name       | CAS No.   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |      |
|------------|-----------------------|-----------|---------------|-------------|----------------|------|
|            |                       |           |               |             | 13R            | 14   |
| 1          | Soluble Antimony (Sb) | 7440-36-0 | 60            | 5           | N.D.           | N.D. |
| 2          | Soluble Arsenic (As)  | 7440-38-2 | 25            | 2.5         | N.D.           | N.D. |
| 3          | Soluble Barium (Ba)   | 7440-39-3 | 1000          | 5           | N.D.           | N.D. |
| 4          | Soluble Cadmium (Cd)  | 7440-43-9 | 75            | 5           | N.D.           | N.D. |
| 5          | Soluble Chromium (Cr) | 7440-47-3 | 60            | 5           | N.D.           | N.D. |
| 6          | Soluble Lead (Pb)     | 7439-92-1 | 90            | 5           | N.D.           | N.D. |
| 7          | Soluble Mercury (Hg)  | 7439-97-6 | 60            | 5           | N.D.           | N.D. |
| 8          | Soluble Selenium (Se) | 7782-49-2 | 500           | 5           | N.D.           | N.D. |
| Conclusion |                       |           |               |             | PASS           | PASS |

| No.        | Substances Name       | CAS No.   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |      |
|------------|-----------------------|-----------|---------------|-------------|----------------|------|
|            |                       |           |               |             | 15             | 16   |
| 1          | Soluble Antimony (Sb) | 7440-36-0 | 60            | 5           | N.D.           | N.D. |
| 2          | Soluble Arsenic (As)  | 7440-38-2 | 25            | 2.5         | N.D.           | N.D. |
| 3          | Soluble Barium (Ba)   | 7440-39-3 | 1000          | 5           | N.D.           | N.D. |
| 4          | Soluble Cadmium (Cd)  | 7440-43-9 | 75            | 5           | N.D.           | N.D. |
| 5          | Soluble Chromium (Cr) | 7440-47-3 | 60            | 5           | N.D.           | N.D. |
| 6          | Soluble Lead (Pb)     | 7439-92-1 | 90            | 5           | N.D.           | N.D. |
| 7          | Soluble Mercury (Hg)  | 7439-97-6 | 60            | 5           | N.D.           | N.D. |
| 8          | Soluble Selenium (Se) | 7782-49-2 | 500           | 5           | N.D.           | N.D. |
| Conclusion |                       |           |               |             | PASS           | PASS |




# Test Report

Report No.:CTT2603031036ENR2

Page 29 of 45

| No.        | Substances Name       | CAS No.   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |      |
|------------|-----------------------|-----------|---------------|-------------|----------------|------|
|            |                       |           |               |             | 17             | 18   |
| 1          | Soluble Antimony (Sb) | 7440-36-0 | 60            | 5           | N.D.           | N.D. |
| 2          | Soluble Arsenic (As)  | 7440-38-2 | 25            | 2.5         | N.D.           | N.D. |
| 3          | Soluble Barium (Ba)   | 7440-39-3 | 1000          | 5           | N.D.           | 6    |
| 4          | Soluble Cadmium (Cd)  | 7440-43-9 | 75            | 5           | N.D.           | N.D. |
| 5          | Soluble Chromium (Cr) | 7440-47-3 | 60            | 5           | N.D.           | N.D. |
| 6          | Soluble Lead (Pb)     | 7439-92-1 | 90            | 5           | N.D.           | N.D. |
| 7          | Soluble Mercury (Hg)  | 7439-97-6 | 60            | 5           | N.D.           | N.D. |
| 8          | Soluble Selenium (Se) | 7782-49-2 | 500           | 5           | N.D.           | N.D. |
| Conclusion |                       |           |               |             | PASS           | PASS |

| No.        | Substances Name       | CAS No.   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |      |
|------------|-----------------------|-----------|---------------|-------------|----------------|------|
|            |                       |           |               |             | 19             | 21   |
| 1          | Soluble Antimony (Sb) | 7440-36-0 | 60            | 5           | N.D.           | N.D. |
| 2          | Soluble Arsenic (As)  | 7440-38-2 | 25            | 2.5         | N.D.           | N.D. |
| 3          | Soluble Barium (Ba)   | 7440-39-3 | 1000          | 5           | 5              | N.D. |
| 4          | Soluble Cadmium (Cd)  | 7440-43-9 | 75            | 5           | N.D.           | N.D. |
| 5          | Soluble Chromium (Cr) | 7440-47-3 | 60            | 5           | N.D.           | N.D. |
| 6          | Soluble Lead (Pb)     | 7439-92-1 | 90            | 5           | N.D.           | N.D. |
| 7          | Soluble Mercury (Hg)  | 7439-97-6 | 60            | 5           | N.D.           | N.D. |
| 8          | Soluble Selenium (Se) | 7782-49-2 | 500           | 5           | N.D.           | N.D. |
| Conclusion |                       |           |               |             | PASS           | PASS |



# Test Report


Report No.:CTT2603031036ENR2

Page 30 of 45

| No.        | Substances Name       | CAS No.   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |      |
|------------|-----------------------|-----------|---------------|-------------|----------------|------|
|            |                       |           |               |             | 22             | 23*  |
| 1          | Soluble Antimony (Sb) | 7440-36-0 | 60            | 5           | 11             | N.D. |
| 2          | Soluble Arsenic (As)  | 7440-38-2 | 25            | 2.5         | N.D.           | N.D. |
| 3          | Soluble Barium (Ba)   | 7440-39-3 | 1000          | 5           | 12             | 17   |
| 4          | Soluble Cadmium (Cd)  | 7440-43-9 | 75            | 5           | N.D.           | N.D. |
| 5          | Soluble Chromium (Cr) | 7440-47-3 | 60            | 5           | N.D.           | N.D. |
| 6          | Soluble Lead (Pb)     | 7439-92-1 | 90            | 5           | N.D.           | N.D. |
| 7          | Soluble Mercury (Hg)  | 7439-97-6 | 60            | 5           | N.D.           | N.D. |
| 8          | Soluble Selenium (Se) | 7782-49-2 | 500           | 5           | N.D.           | N.D. |
| Conclusion |                       |           |               |             | PASS           | PASS |

| No.        | Substances Name       | CAS No.   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |      |
|------------|-----------------------|-----------|---------------|-------------|----------------|------|
|            |                       |           |               |             | 24*            | 27R  |
| 1          | Soluble Antimony (Sb) | 7440-36-0 | 60            | 5           | N.D.           | N.D. |
| 2          | Soluble Arsenic (As)  | 7440-38-2 | 25            | 2.5         | N.D.           | N.D. |
| 3          | Soluble Barium (Ba)   | 7440-39-3 | 1000          | 5           | N.D.           | N.D. |
| 4          | Soluble Cadmium (Cd)  | 7440-43-9 | 75            | 5           | N.D.           | N.D. |
| 5          | Soluble Chromium (Cr) | 7440-47-3 | 60            | 5           | N.D.           | N.D. |
| 6          | Soluble Lead (Pb)     | 7439-92-1 | 90            | 5           | N.D.           | N.D. |
| 7          | Soluble Mercury (Hg)  | 7439-97-6 | 60            | 5           | N.D.           | N.D. |
| 8          | Soluble Selenium (Se) | 7782-49-2 | 500           | 5           | N.D.           | N.D. |
| Conclusion |                       |           |               |             | PASS           | PASS |

**NOTE:** 1. mg/kg = milligram per kilogram (ppm).



# Test Report

Report No.:CTT2603031036ENR2

Page 31 of 45

2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).
3. "R" = The test result is referred from identical material of other report according to applicant's request.
4. 6R = This data is refer to data of CTT2603031035EN-10.
5. 13R = This data is refer to data of CTT2603031033EN-3.
6. 12R = This data is refer to data of CTT2603031033EN-2.
7. 27R = This data is refer to data of CTT2603031033EN-12.
8. "\*" = The test sample(s) is received on Mar. 24, 2026.

## Test Result(s):


Total Lead (Pb) in accessible substrate materials - US Public Law 110-314 [Consumer Product Safety Improvement Act of 2008(CPSIA) Sec. 101] and 15 U.S.C. § 1278a

Method: CPSC-CH-E1002-08.3

| Substances    | Pb             | Conclusion |
|---------------|----------------|------------|
| CAS No.       | 7439-92-1      |            |
| LOQ (mg/kg)   | 10             |            |
| Limit (mg/kg) | 100            |            |
| Material No.  | Result (mg/kg) |            |
| 6R            | N.D.           | PASS       |
| 13R           | N.D.           | PASS       |
| 14            | N.D.           | PASS       |
| 15            | N.D.           | PASS       |
| 16            | N.D.           | PASS       |
| 18+21         | N.D.           | PASS       |
| 23+24*        | N.D.           | PASS       |
| 27R           | N.D.           | PASS       |

## NOTE:

1. mg/kg = milligram per kilogram (ppm).
2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).
3. "+" = The "+" in the test sample description indicates a mixed test. The test results are the overall results of the mixed materials. The individual result of one or more materials in the mixed material may be greater than the mixed test result. Conclusion of compliance also applies to the individual materials in a mixed test only if multiplying the LOQ (Limit of Quantitation) and the number of mixed materials is less than the limit.
4. "R" = The test result is referred from identical material of other report according to applicant's request.
5. 6R = This data is refer to data of CTT2603031035EN-10.
6. 13R = This data is refer to data of CTT2603031033EN-3.
7. 27R = This data is refer to data of CTT2603031033EN-12.
8. "\*" = The test sample(s) is received on Mar. 24, 2026.



# Test Report

Report No.:CTT2603031036ENR2

Page 32 of 45


## Test Result(s):

Total Lead - ASTM F963-23 Section 4.3 Toxicology 4.3.5.2 Non-metallic Materials

| Substances    | Pb             | Conclusion |
|---------------|----------------|------------|
| CAS No.       | 7439-92-1      |            |
| LOQ (mg/kg)   | 10             |            |
| Limit (mg/kg) | 100            |            |
| Material No.  | Result (mg/kg) |            |
| 6R            | N.D.           | PASS       |
| 13R           | N.D.           | PASS       |
| 14D           | N.D.           | PASS       |
| 15D           | N.D.           | PASS       |
| 16D           | N.D.           | PASS       |
| (18+21)D      | N.D.           | PASS       |
| (23+24)D*     | N.D.           | PASS       |
| 27R           | N.D.           | PASS       |

## NOTE:

1. mg/kg = milligram per kilogram (ppm).
2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).
3. "+" = The "+" in the test sample description indicates a mixed test. The test results are the overall results of the mixed materials. The individual result of one or more materials in the mixed material may be greater than the mixed test result. Conclusion of compliance also applies to the individual materials in a mixed test only if multiplying the LOQ (Limit of Quantitation) and the number of mixed materials is less than the limit.
4. "R" = The test result is referred from identical material of other report according to applicant's request.
5. 6R = This data is refer to data of CTT2603031035EN-10.
6. 13R = This data is refer to data of CTT2603031033EN-3.
7. 27R = This data is refer to data of CTT2603031033EN-12.
8. "D" = The sample(s) is(are) tested according to the method CPSC-CH-E1002-08.3.
9. "\*" = The test sample(s) is received on Mar. 24, 2026.



# Test Report


Report No.:CTT2603031036ENR2

Page 33 of 45

## Test Result(s):

Phthalates - ASTM F963-23, Section 4.3 Toxicology 4.3.8 Accessible plasticized component

| No.        | Substances Name                                          | CAS No.                   | Limit<br>(mg/kg) | LOQ<br>(mg/kg) | Result (mg/kg) |      |
|------------|----------------------------------------------------------|---------------------------|------------------|----------------|----------------|------|
|            |                                                          |                           |                  |                | 6R             | 13R  |
| 1          | Bis(2-ethylhexyl)<br>phthalate (DEHP)                    | 117-81-7                  | 1000             | 50             | N.D.           | N.D. |
| 2          | Butyl benzyl<br>phthalate (BBP)                          | 85-68-7                   | 1000             | 50             | N.D.           | N.D. |
| 3          | Di-butyl phthalate<br>(DBP)                              | 84-74-2                   | 1000             | 50             | N.D.           | N.D. |
| 4          | Di-cyclohexyl<br>phthalate (DCHP)                        | 84-61-7                   | 1000             | 50             | N.D.           | N.D. |
| 5          | Di-iso-butyl<br>phthalate (DIBP)                         | 84-69-5                   | 1000             | 50             | N.D.           | N.D. |
| 6          | Diisononyl phthalate<br>(DINP)                           | 28553-12-0/<br>68515-48-0 | 1000             | 100            | N.D.           | N.D. |
| 7          | Phthalic acid,<br>bis-hexyl ester<br>(DNHP/DHEXP/DHP)    | 84-75-3                   | 1000             | 50             | N.D.           | N.D. |
| 8          | Phthalic acid,<br>bis-n-pentyl ester<br>(DPP/DPENP/DnPP) | 131-18-0                  | 1000             | 50             | N.D.           | N.D. |
| Conclusion |                                                          |                           |                  |                | PASS           | PASS |




# Test Report

Report No.:CTT2603031036ENR2

Page 34 of 45

| No.        | Substances Name                                          | CAS No.                   | Limit<br>(mg/kg) | LOQ<br>(mg/kg) | Result (mg/kg) |      |
|------------|----------------------------------------------------------|---------------------------|------------------|----------------|----------------|------|
|            |                                                          |                           |                  |                | 14D            | 15D  |
| 1          | Bis(2-ethylhexyl)<br>phthalate (DEHP)                    | 117-81-7                  | 1000             | 50             | 112            | N.D. |
| 2          | Butyl benzyl<br>phthalate (BBP)                          | 85-68-7                   | 1000             | 50             | N.D.           | N.D. |
| 3          | Di-butyl phthalate<br>(DBP)                              | 84-74-2                   | 1000             | 50             | N.D.           | N.D. |
| 4          | Di-cyclohexyl<br>phthalate (DCHP)                        | 84-61-7                   | 1000             | 50             | N.D.           | N.D. |
| 5          | Di-iso-butyl<br>phthalate (DIBP)                         | 84-69-5                   | 1000             | 50             | N.D.           | N.D. |
| 6          | Diisononyl<br>phthalate (DINP)                           | 28553-12-0/<br>68515-48-0 | 1000             | 100            | N.D.           | N.D. |
| 7          | Phthalic acid,<br>bis-hexyl ester<br>(DNHP/DHEXP/DHP)    | 84-75-3                   | 1000             | 50             | N.D.           | N.D. |
| 8          | Phthalic acid,<br>bis-n-pentyl ester<br>(DPP/DPENP/DnPP) | 131-18-0                  | 1000             | 50             | N.D.           | N.D. |
| Conclusion |                                                          |                           |                  |                | PASS           | PASS |




# Test Report

Report No.:CTT2603031036ENR2

Page 35 of 45

| No.        | Substances Name                                          | CAS No.                   | Limit<br>(mg/kg) | LOQ<br>(mg/kg) | Result (mg/kg) |          |
|------------|----------------------------------------------------------|---------------------------|------------------|----------------|----------------|----------|
|            |                                                          |                           |                  |                | 16D            | (18+21)D |
| 1          | Bis(2-ethylhexyl)<br>phthalate (DEHP)                    | 117-81-7                  | 1000             | 50             | N.D.           | N.D.     |
| 2          | Butyl benzyl<br>phthalate (BBP)                          | 85-68-7                   | 1000             | 50             | N.D.           | N.D.     |
| 3          | Di-butyl phthalate<br>(DBP)                              | 84-74-2                   | 1000             | 50             | N.D.           | N.D.     |
| 4          | Di-cyclohexyl<br>phthalate (DCHP)                        | 84-61-7                   | 1000             | 50             | N.D.           | N.D.     |
| 5          | Di-iso-butyl<br>phthalate (DIBP)                         | 84-69-5                   | 1000             | 50             | N.D.           | N.D.     |
| 6          | Diisononyl<br>phthalate (DINP)                           | 28553-12-0/<br>68515-48-0 | 1000             | 100            | N.D.           | N.D.     |
| 7          | Phthalic acid,<br>bis-hexyl ester<br>(DNHP/DHEXP/DHP)    | 84-75-3                   | 1000             | 50             | N.D.           | N.D.     |
| 8          | Phthalic acid,<br>bis-n-pentyl ester<br>(DPP/DPENP/DnPP) | 131-18-0                  | 1000             | 50             | N.D.           | N.D.     |
| Conclusion |                                                          |                           |                  |                | PASS           | PASS     |




# Test Report

Report No.:CTT2603031036ENR2

Page 36 of 45

| No.        | Substances Name                                          | CAS No.                   | Limit<br>(mg/kg) | LOQ<br>(mg/kg) | Result (mg/kg) |      |
|------------|----------------------------------------------------------|---------------------------|------------------|----------------|----------------|------|
|            |                                                          |                           |                  |                | (23+24)D*      | 25D  |
| 1          | Bis(2-ethylhexyl)<br>phthalate (DEHP)                    | 117-81-7                  | 1000             | 50             | 143            | 72   |
| 2          | Butyl benzyl<br>phthalate (BBP)                          | 85-68-7                   | 1000             | 50             | N.D.           | N.D. |
| 3          | Di-butyl phthalate<br>(DBP)                              | 84-74-2                   | 1000             | 50             | N.D.           | 225  |
| 4          | Di-cyclohexyl<br>phthalate (DCHP)                        | 84-61-7                   | 1000             | 50             | N.D.           | N.D. |
| 5          | Di-iso-butyl<br>phthalate (DIBP)                         | 84-69-5                   | 1000             | 50             | N.D.           | N.D. |
| 6          | Diisononyl<br>phthalate (DINP)                           | 28553-12-0/<br>68515-48-0 | 1000             | 100            | N.D.           | N.D. |
| 7          | Phthalic acid,<br>bis-hexyl ester<br>(DNHP/DHEXP/DHP)    | 84-75-3                   | 1000             | 50             | N.D.           | N.D. |
| 8          | Phthalic acid,<br>bis-n-pentyl ester<br>(DPP/DPENP/DnPP) | 131-18-0                  | 1000             | 50             | N.D.           | N.D. |
| Conclusion |                                                          |                           |                  |                | PASS           | PASS |




# Test Report

Report No.:CTT2603031036ENR2

Page 37 of 45

| No.        | Substances Name                                    | CAS No.                   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |
|------------|----------------------------------------------------|---------------------------|---------------|-------------|----------------|
|            |                                                    |                           |               |             | 27R            |
| 1          | Bis(2-ethylhexyl) phthalate (DEHP)                 | 117-81-7                  | 1000          | 50          | N.D.           |
| 2          | Butyl benzyl phthalate (BBP)                       | 85-68-7                   | 1000          | 50          | N.D.           |
| 3          | Di-butyl phthalate (DBP)                           | 84-74-2                   | 1000          | 50          | N.D.           |
| 4          | Di-cyclohexyl phthalate (DCHP)                     | 84-61-7                   | 1000          | 50          | N.D.           |
| 5          | Di-iso-butyl phthalate (DIBP)                      | 84-69-5                   | 1000          | 50          | N.D.           |
| 6          | Diisononyl phthalate (DINP)                        | 28553-12-0/<br>68515-48-0 | 1000          | 100         | N.D.           |
| 7          | Phthalic acid, bis-hexyl ester (DNHP/DHEXP/DHP)    | 84-75-3                   | 1000          | 50          | N.D.           |
| 8          | Phthalic acid, bis-n-pentyl ester (DPP/DPENP/DnPP) | 131-18-0                  | 1000          | 50          | N.D.           |
| Conclusion |                                                    |                           |               |             | PASS           |

- NOTE:**
1. mg/kg = milligram per kilogram (ppm).
  2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).
  3. "+" = The "+" in the test sample description indicates a mixed test. The test results are the overall results of the mixed materials. The individual result of one or more materials in the mixed material may be greater than the mixed test result. Conclusion of compliance also applies to the individual materials in a mixed test only if multiplying the LOQ (Limit of Quantitation) and the number of mixed materials is less than the limit.
  4. "R" = The test result is referred from identical material of other report according to applicant's request.
  5. 6R = This data is refer to data of CTT2603031035EN-10.
  6. 13R = This data is refer to data of CTT2603031033EN-3.
  7. 27R = This data is refer to data of CTT2603031033EN-12.
  8. "D" = The sample(s) is(are) tested according to the method CPSC-CH-C1001-09.4 (2018).
  9. "\*" = The test sample(s) is received on Mar. 24, 2026.



# Test Report

Report No.:CTT2603031036ENR2


Page 38 of 45

## Test Result(s):

Phthalates - US Public Law 110-314 [Consumer Product Safety Improvement Act of 2008(CPSIA) Sec. 108] and CPSC 16 CFR 1307

Method: CPSC-CH-C1001-09.4 (2018)

| No.        | Substances Name                                    | CAS No.                   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |      |
|------------|----------------------------------------------------|---------------------------|---------------|-------------|----------------|------|
|            |                                                    |                           |               |             | 6R             | 13R  |
| 1          | Bis(2-ethylhexyl) phthalate (DEHP)                 | 117-81-7                  | 1000          | 50          | N.D.           | N.D. |
| 2          | Butyl benzyl phthalate (BBP)                       | 85-68-7                   | 1000          | 50          | N.D.           | N.D. |
| 3          | Di-butyl phthalate (DBP)                           | 84-74-2                   | 1000          | 50          | N.D.           | N.D. |
| 4          | Di-cyclohexyl phthalate (DCHP)                     | 84-61-7                   | 1000          | 50          | N.D.           | N.D. |
| 5          | Di-iso-butyl phthalate (DIBP)                      | 84-69-5                   | 1000          | 50          | N.D.           | N.D. |
| 6          | Diisononyl phthalate (DINP)                        | 28553-12-0/<br>68515-48-0 | 1000          | 100         | N.D.           | N.D. |
| 7          | Phthalic acid, bis-hexyl ester (DNHP/DHEXP/DHP)    | 84-75-3                   | 1000          | 50          | N.D.           | N.D. |
| 8          | Phthalic acid, bis-n-pentyl ester (DPP/DPENP/DnPP) | 131-18-0                  | 1000          | 50          | N.D.           | N.D. |
| Conclusion |                                                    |                           |               |             | PASS           | PASS |




# Test Report

Report No.:CTT2603031036ENR2

Page 39 of 45

| No.        | Substances Name                                          | CAS No.                   | Limit<br>(mg/kg) | LOQ<br>(mg/kg) | Result (mg/kg) |      |
|------------|----------------------------------------------------------|---------------------------|------------------|----------------|----------------|------|
|            |                                                          |                           |                  |                | 14             | 15   |
| 1          | Bis(2-ethylhexyl)<br>phthalate (DEHP)                    | 117-81-7                  | 1000             | 50             | 112            | N.D. |
| 2          | Butyl benzyl<br>phthalate (BBP)                          | 85-68-7                   | 1000             | 50             | N.D.           | N.D. |
| 3          | Di-butyl phthalate<br>(DBP)                              | 84-74-2                   | 1000             | 50             | N.D.           | N.D. |
| 4          | Di-cyclohexyl<br>phthalate (DCHP)                        | 84-61-7                   | 1000             | 50             | N.D.           | N.D. |
| 5          | Di-iso-butyl<br>phthalate (DIBP)                         | 84-69-5                   | 1000             | 50             | N.D.           | N.D. |
| 6          | Diisononyl<br>phthalate (DINP)                           | 28553-12-0/<br>68515-48-0 | 1000             | 100            | N.D.           | N.D. |
| 7          | Phthalic acid,<br>bis-hexyl ester<br>(DNHP/DHEXP/DHP)    | 84-75-3                   | 1000             | 50             | N.D.           | N.D. |
| 8          | Phthalic acid,<br>bis-n-pentyl ester<br>(DPP/DPENP/DnPP) | 131-18-0                  | 1000             | 50             | N.D.           | N.D. |
| Conclusion |                                                          |                           |                  |                | PASS           | PASS |




# Test Report

Report No.:CTT2603031036ENR2

Page 40 of 45

| No.        | Substances Name                                    | CAS No.                   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |       |
|------------|----------------------------------------------------|---------------------------|---------------|-------------|----------------|-------|
|            |                                                    |                           |               |             | 16             | 18+21 |
| 1          | Bis(2-ethylhexyl) phthalate (DEHP)                 | 117-81-7                  | 1000          | 50          | N.D.           | N.D.  |
| 2          | Butyl benzyl phthalate (BBP)                       | 85-68-7                   | 1000          | 50          | N.D.           | N.D.  |
| 3          | Di-butyl phthalate (DBP)                           | 84-74-2                   | 1000          | 50          | N.D.           | N.D.  |
| 4          | Di-cyclohexyl phthalate (DCHP)                     | 84-61-7                   | 1000          | 50          | N.D.           | N.D.  |
| 5          | Di-iso-butyl phthalate (DIBP)                      | 84-69-5                   | 1000          | 50          | N.D.           | N.D.  |
| 6          | Diisononyl phthalate (DINP)                        | 28553-12-0/<br>68515-48-0 | 1000          | 100         | N.D.           | N.D.  |
| 7          | Phthalic acid, bis-hexyl ester (DNHP/DHEXP/DHP)    | 84-75-3                   | 1000          | 50          | N.D.           | N.D.  |
| 8          | Phthalic acid, bis-n-pentyl ester (DPP/DPENP/DnPP) | 131-18-0                  | 1000          | 50          | N.D.           | N.D.  |
| Conclusion |                                                    |                           |               |             | PASS           | PASS  |




# Test Report

Report No.:CTT2603031036ENR2

Page 41 of 45

| No.        | Substances Name                                    | CAS No.                   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |      |
|------------|----------------------------------------------------|---------------------------|---------------|-------------|----------------|------|
|            |                                                    |                           |               |             | 23+24*         | 25   |
| 1          | Bis(2-ethylhexyl) phthalate (DEHP)                 | 117-81-7                  | 1000          | 50          | 143            | 72   |
| 2          | Butyl benzyl phthalate (BBP)                       | 85-68-7                   | 1000          | 50          | N.D.           | N.D. |
| 3          | Di-butyl phthalate (DBP)                           | 84-74-2                   | 1000          | 50          | N.D.           | 225  |
| 4          | Di-cyclohexyl phthalate (DCHP)                     | 84-61-7                   | 1000          | 50          | N.D.           | N.D. |
| 5          | Di-iso-butyl phthalate (DIBP)                      | 84-69-5                   | 1000          | 50          | N.D.           | N.D. |
| 6          | Diisononyl phthalate (DINP)                        | 28553-12-0/<br>68515-48-0 | 1000          | 100         | N.D.           | N.D. |
| 7          | Phthalic acid, bis-hexyl ester (DNHP/DHEXP/DHP)    | 84-75-3                   | 1000          | 50          | N.D.           | N.D. |
| 8          | Phthalic acid, bis-n-pentyl ester (DPP/DPENP/DnPP) | 131-18-0                  | 1000          | 50          | N.D.           | N.D. |
| Conclusion |                                                    |                           |               |             | PASS           | PASS |




# Test Report

Report No.:CTT2603031036ENR2

Page 42 of 45

| No.        | Substances Name                                    | CAS No.                   | Limit (mg/kg) | LOQ (mg/kg) | Result (mg/kg) |
|------------|----------------------------------------------------|---------------------------|---------------|-------------|----------------|
|            |                                                    |                           |               |             | 27R            |
| 1          | Bis(2-ethylhexyl) phthalate (DEHP)                 | 117-81-7                  | 1000          | 50          | N.D.           |
| 2          | Butyl benzyl phthalate (BBP)                       | 85-68-7                   | 1000          | 50          | N.D.           |
| 3          | Di-butyl phthalate (DBP)                           | 84-74-2                   | 1000          | 50          | N.D.           |
| 4          | Di-cyclohexyl phthalate (DCHP)                     | 84-61-7                   | 1000          | 50          | N.D.           |
| 5          | Di-iso-butyl phthalate (DIBP)                      | 84-69-5                   | 1000          | 50          | N.D.           |
| 6          | Diisononyl phthalate (DINP)                        | 28553-12-0/<br>68515-48-0 | 1000          | 100         | N.D.           |
| 7          | Phthalic acid, bis-hexyl ester (DNHP/DHEXP/DHP)    | 84-75-3                   | 1000          | 50          | N.D.           |
| 8          | Phthalic acid, bis-n-pentyl ester (DPP/DPENP/DnPP) | 131-18-0                  | 1000          | 50          | N.D.           |
| Conclusion |                                                    |                           |               |             | PASS           |

- NOTE:**
1. mg/kg = milligram per kilogram (ppm).
  2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).
  3. "+" = The "+" in the test sample description indicates a mixed test. The test results are the overall results of the mixed materials. The individual result of one or more materials in the mixed material may be greater than the mixed test result. Conclusion of compliance also applies to the individual materials in a mixed test only if multiplying the LOQ (Limit of Quantitation) and the number of mixed materials is less than the limit.
  4. "R" = The test result is referred from identical material of other report according to applicant's request.
  5. 6R = This data is refer to data of CTT2603031035EN-10.
  6. 13R = This data is refer to data of CTT2603031033EN-3.
  7. 27R = This data is refer to data of CTT2603031033EN-12.
  8. "\*" = The test sample(s) is received on Mar. 24, 2026.



# Test Report

Report No.:CTT2603031036ENR2


Page 43 of 45

## Test Material List

| Material No. | Sample Description                                                        | Location                 |
|--------------|---------------------------------------------------------------------------|--------------------------|
| 1            | Green synthetic fiber                                                     | Skirt body               |
| 2            | White synthetic fiber                                                     | Front of collar          |
| 3            | White synthetic fiber                                                     | Back of collar           |
| 4*           | Red synthetic fiber                                                       | Pom pom                  |
| 5            | White synthetic fiber                                                     | Small pom pom            |
| 6            | Black synthetic fiber with black rubber                                   | Small elastic rope       |
| 7            | Red synthetic fiber                                                       | Hat body                 |
| 8            | White non-woven                                                           | Inside of hat            |
| 9            | Black non-woven                                                           | Inside of hat brim       |
| 10           | White synthetic fiber                                                     | Lace                     |
| 11*          | White non-woven                                                           | Wafer                    |
| 12           | Black synthetic fiber                                                     | Velcro                   |
| 13           | Black plastic                                                             | Velcro                   |
| 14           | Black synthetic with black synthetic fiber                                | Belt                     |
| 15           | White plastic with golden/silvery plating                                 | Buckle ring              |
| 16           | Red synthetic fiber with yellow rubber                                    | Sock mouth               |
| 17           | Red/white synthetic fiber                                                 | Sock body                |
| 18*          | White synthetic fiber with green/silvery plastic                          | Front of leaf            |
| 19*          | Green synthetic fiber                                                     | Back of leaf             |
| 20*          | Beige white foam                                                          | Interlayer of leaf       |
| 21           | Red synthetic fiber with white rubber                                     | Large elastic rope       |
| 22           | Red non-woven                                                             | Shoe                     |
| 23           | White plastic                                                             | Walking stick            |
| 24           | Beige white transparent plastic                                           | Air cock                 |
| 25*          | Red paint                                                                 | Coating of walking stick |
| 26           | Costume suit                                                              | Costume suit individual  |
| 27           | White synthetic fiber with black synthetic fiber with red synthetic fiber | Label                    |

**Note:** The testing material(s) marked "\*" was (were) taken from components/raw material(s).

Remark: This report supersedes CTT2603031036ENR1 which is withdrawn.




# Test Report

Report No.:CTT2603031036ENR2

Page 44 of 45


Photo of Sample:



# Test Report

Report No.:CTT2603031036ENR2

Page 45 of 45



\*\*\*End of Report\*\*\*

This test report is issued by the company subject to its General Conditions of Services and accessible at <http://www.cttlab.com/order/202103190908290166.pdf>. The sample and sample information are provided by the applicant, our company are not responsible for their integrity and authenticity. Unless otherwise stated the results shown in this report only apply to the sample as received. Any inquiry about this report, please raise from the date of receipt of the report within 30 days, overdue will not be accept. Without prior written permission of the company, this test report cannot be reproduced, except in full. Items marked with "n" means they are not accredited by CNAS (if with CNAS logo), "s" means the item of subcontractor. This report is only used for scientific research, teaching, internal quality control, not for domestic social impartiality proof data.

